

RedRingSolder®

www.redringsolder.com Email: info@redringsolder.com

RedRing Solder (Malaysia) Sdn Bhd (56167-X)

Lot 17486, Jalan Dua, Taman Selayang Baru, 68100 Batu Caves, Selangor, Malaysia. Tel: 603 6138 5757 Fax: 603 6138 1010

OUALITY ASSURANCE REPORT

Customer

TOP ELECTRONICS COMPONENT SA

Description

LEAD FREE SOLDER BAR XB-G220-B20

Specification

JIS Z 3282 STANDARD

Q.C. Number

SB-1631-2015

1508646

Compliance

Lot Number

14-09-2015

Date

ELEMENT	RESULTS	SPECIFICATION
Sn	96.48%	96.5% ± 0.5
Pb	0.028%	0.05%MAX
Sb	0.011%	0.12%MAX
Cu	0.504%	0.5 ± 0.2
Zn	0.00027%	0.002%MAX
Fe	0.0028%	0.02%MAX
Al	0.00074%	0.002%MAX
As	0.013%	0.03%MAX
Cd	<0.00010%	0.002%MAX
Bi	0.0016%	0.10%MAX
Ag	2.94%	3.0 %± 0.2

ELEMENT	RESULTS	SPECIFICATION
Au	<0.00010%	0.005%MAX
Ni	0.0038%	0.005%MAX
În	0.0015%	0.005%MAX

The analysis was established by calculating the arithmetic average of three uniform sputters created on the analyzed sample by an extremely stable spark source. The equipment used to perform the analysis was a Spectrolab Instrument Model M7/8 manufactured by the Spectro Analytical Instrument, USA.

Prepared by:

Q. C. INSPECTOR

Checked by:

The information contained herein is based on data considered accurate. No warranty is expressed or implied regarding the accuracy of this data. Liability is expressly disclaimed for any loss or injury arising out of this information or the use of any material designated.

